

Membrane Switch Products with Adhesive 200MP

7945MP • 7952MP • 7953MP • 7955MP • 7956MP

7957MP • 7959MP • 7961MP • 7962MP • 7965MP

7993MP • 7995MP • 7997MP • 9045MP • 9056MP

9057MP • 9059MP • 9061MP

Technical Data October, 2013

Product Description

3MTM High Performance Acrylic Adhesive 200MP is a popular choice, and industry standard, for graphic attachment and general industrial joining applications. It provides outstanding adhesion to metal and high surface energy plastics. This adhesive provides some initial repositionability for placement accuracy when bonding to plastics. It also performs well after exposure to humidity and hot/cold cycles and provides the assurance the switch will perform through difficult environmental conditions and millions of actuations.

- Up to 400°F short-term heat resistance
- Excellent solvent resistance
- Excellent shear strength to resist slippage and edge lifting

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Construction Information

3M[™] Double Linered 200MP Adhesive Transfer Tape products offer:


- High adhesive strength for a long-lasting durable bond
- High cohesive strength to resist lifting and separation especially in harsh environments
- Smooth adhesive for a uniform graphic appearance
- Environmental stability for a long-aging performance
- Moisture stable liner for easy, layflat processing
- Easy differential release liners for fast, consistent processing



Product	Adhesive Thickness mils (mm)	Liner 1 Type Liner 1 Thickness mils (mm)	Liner 2 Type Liner 2 Thickness mils (mm)
7952MP	2.0 mils	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)
	(0.05 mm)	4.2 mils (0.11 mm)	4.2 mils (0.11 mm)
7962MP	2.0 mils	58# Polycoated Kraft Paper (PCK)	83# Polycoated Kraft Paper (PCK)
73021411	(0.05 mm)	4.2 mils (0.11 mm)	6.2 mils (0.16 mm)
7955MP	5.0 mils	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)
7933WIF	(0.13 mm)	4.2 mils (0.11 mm)	4.2 mils (0.11 mm)
ZOCEMB	5.0 mils	58# Polycoated Kraft Paper (PCK)	83# Polycoated Kraft Paper (PCK)
7965MP	(0.13 mm)	4.2 mils (0.11 mm)	6.2 mils (0.16 mm)

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Construction Information (continued) 3MTM Double Coated Membrane Switch Spacers feature 2.0 or 5.0 mil adhesive layers for industry-standard, high-performance requirements.



Product	Adhesive 1 Thickness mils (mm)	Carrier Type Carrier Thickness mils (mm)	Adhesive 2 Thickness mils (mm)	Liner 1 Type Liner Thickness mils (mm)	Liner 2 Type Liner Thickness mils (mm)
7953MP	1.5 mils (0.04 mm)	Polyester Film (PET) 0.5 mils (0.01 mm)	1.5 mils (0.04 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)
7945MP	2.0 mils (0.05 mm)	Polyester Film (PET) 1.0 mils (0.03 mm)	2.0 mils (0.05 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)
7956MP	2.0 mils (0.05 mm)	Polyester Film (PET) 2.0 mils (0.05 mm)	2.0 mils (0.05 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)
7957MP	2.0 mils (0.05 mm)	Polyester Film (PET) 3.0 mils (0.08 mm)	2.0 mils (0.05 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)
7959MP	2.0 mils (0.05 mm)	Polyester Film (PET) 5.0 mils (0.13 mm)	2.0 mils (0.05 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Construction Information (continued)	Product	Adhesive 1 Thickness mils (mm)	Carrier Type Carrier Thickness mils (mm)	Adhesive 2 Thickness mils (mm)	Liner 1 Type Liner Thickness mils (mm)	Liner 2 Type Liner Thickness mils (mm)
	7961MP	2.0 mils (0.05 mm)	Polyester Film (PET) 7.0 mils (0.18 mm)	2.0 mils (0.05 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)	58# Polycoated Kraft Paper (PCK) 4.2 mils (0.11 mm)
	9045MP	2.0 mils (0.05 mm)	Polyester Film (PET) 1.0 mils (0.03 mm)	2.0 mils (0.05 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)
	9056MP	2.0 mils (0.05 mm)	Polyester Film (PET) 2.0 mils (0.05 mm)	2.0 mils (0.05 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)
	9057MP	2.0 mils (0.05 mm)	Polyester Film (PET) 3.0 mils (0.08 mm)	2.0 mils (0.05 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)
	9059MP	2.0 mils (0.05 mm)	Polyester Film (PET) 5.0 mils (0.13 mm)	2.0 mils (0.05 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)
	9061MP	2.0 mils (0.05 mm)	Polyester Film (PET) 7.0 mils (0.18 mm)	2.0 mils (0.05 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)	94# Polycoated Kraft Paper (PCK) 7.0 mils (0.18 mm)

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Construction Information (continued)

3MTM Single Coated Membrane Switch Spacers offer:

- Smooth adhesive layer for consistent actuation and excellent sealability of switch
- High adhesive strength to resist moisture penetration, and environmental conditions
- High cohesive strength to resist lifting and separation especially in harsh environments
- High temperature resistance to resist splitting in harsh environments
- High chemical resistance to resist contamination of contacts in harsh environments
- Heat stabilized polyester for dimensional stability through broad temperature range
- Moisture stable liners for easy, layflat processing
- Easy liner release for fast, consistent processing



Product	Adhesive Thickness mils (mm)	Carrier Type Carrier Thickness mils (mm)	Liner 1 Type Liner Thickness mils (mm)
7002MP	2.0 mils		58# Polycoated Kraft Paper (PCK)
7993MP	(0.05 mm)	1.0 mils (0.03 mm)	4.2 mils (0.11 mm)
	2.0 mils	Polyester Film (PET)	58# Polycoated Kraft Paper (PCK)
7995MP	(0.05 mm)	3.0 mils (0.08 mm)	4.2 mils (0.11 mm)
	2.0 mils	Polyester Film (PET)	58# Polycoated Kraft Paper (PCK)
7997MP	(0.05 mm)	5.0 mils (0.13 mm)	4.2 mils (0.11 mm)

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics

3M™ Double Linered Adhesive Transfer Tapes (for selective die cutting)

3M™ Membrane		Peel Adhesion ASTM D3330, Modified 90° Peel				
Switch	Adhesive Family		Initial (20 minutes)	72 hours @ 72°F (22°C)	72 hours @ 158°F (70°C)	
Product Number	,	Film / Substrate	Typical Value oz/in (N/25mm)	Typical Value oz/in (N/25mm)	Typical Value oz/in (N/25mm)	
7952MP	200MP	PET/Stainless Steel	31 (9)	97 (27)	156 (43)	
7962MP		PET/Aluminum	41 (11)	76 (21)	157 (43)	
(2-0-0)		PET/PET	38 (11)	66 (18)	118 (33)	
		PET/Polycarbonate	43 (12)	70 (19)	67 (19)	
7953MP	200MP	PET/Stainless Steel	50 (14)	113 (31)	160 (44)	
(1.5-0.5-1.5)		PET/Aluminum	32 (9)	75 (21)	152 (42)	
		PET/PET	44 (12)	73 (20)	125 (35)	
		PET/Polycarbonate	47 (13)	76 (21)	75 (21)	
7955MP	200MP	PET/Stainless Steel	69 (19)	112 (31)	167 (46)	
7965MP		PET/Aluminum	77 (21)	115 (32)	169 (47)	
(5-0-0)		PET/PET	77 (21)	95 (26)	164 (45)	
		PET/Polycarbonate	84 (23)	102 (28)	94 (26)	

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Double Coated Membrane Switch Spacers (for circuit separation)

3 M ™			Peel Adhesion ASTM D3330, Modified 90° Peel				
Membrane Switch	Adhesive Family		Initial (20 minutes)	72 hours @ 72°F (22°C)	72 hours @ 158°F (70°C)		
Product Number	. alliny	Film / Substrate	Typical Value	Typical Value	Typical Value		
			oz/in (N/25mm)	oz/in (N/25mm)	oz/in (N/25mm)		
7945MP	200MP	PET/Stainless Steel	64 (18)	112 (31)	165 (45)		
9045MP		PET/Aluminum	42 (12)	84 (23)	168 (56)		
(2-1-2)		PET/PET	49 (14)	67 (19)	126 (35)		
		PET/Polycarbonate	50 (14)	72 (20)	84 (23)		
7956MP	200MP	PET/Stainless Steel	50 (14)	113 (31)	156 (43)		
9056MP		PET/Aluminum	32 (9)	75 (21)	157 (43)		
(2-2-2)		PET/PET	44 (12)	73 (20)	118 (33)		
		PET/Polycarbonate	47 (13)	76 (21)	67 (19)		
7957MP	200MP	PET/Stainless Steel	54 (15)	95 (26)	153 (42)		
9057MP		PET/Aluminum	66 (25)	73 (20)	148 (41)		
(2-3-2)		PET/PET	37 (10)	60 (17)	136 (38)		
		PET/Polycarbonate	41 (11)	66 (18)	72 (20)		
7959MP	200MP	PET/Stainless Steel	30 (8)	83 (23)	134 (37)		
9059MP		PET/Aluminum	31 (9)	68 (19)	124 (31)		
(2-5-2)		PET/PET	33 (9)	53 (15)	118 (33)		
		PET/Polycarbonate	36 (10)	54 (15)	66 (18)		
7961MP	200MP	PET/Stainless Steel	30 (8)	101 (28)	135 (37)		
9061MP		PET/Aluminum	30 (8)	70 (20)	134 (37)		
(2-7-2)		PET/PET	35 (10)	61 (17)	124 (31)		
		PET/Polycarbonate	37 (10)	55 (15)	67 (19)		

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Single Coated Membrane Switch Spacers (for circuit separation)

3М™		Peel Adhesion ASTM D3330, Modified 90° Peel				
Membrane Switch	Adhesive Family		Initial (20 minutes)	72 hours @ 72°F (22°C)	72 hours @ 158°F (70°C)	
Product Number		Film / Substrate	Typical Value oz/in (N/25mm)	Typical Value oz/in (N/25mm)	Typical Value oz/in (N/25mm)	
7993MP	200MP	PET/Stainless Steel	40 (11)	68 (19)	82 (23)	
(2-1-0)		PET/Aluminum	36 (10)	64 (18)	79 (22)	
(2 : 0)		PET/PET	36 (10)	46 (13)	72 (20)	
		PET/Polycarbonate	38 (11)	51 (14)	62 (17)	
7995MP	200MP	PET/Stainless Steel	33 (9)	73 (20)	148 (41)	
(2-3-0)		PET/Aluminum	48 (13)	84 (23)	186 (51)	
(= 5 5)		PET/PET	44 (12)	63 (17)	195 (53)	
		PET/Polycarbonate	42 (12)	64 (18)	147 (41)	
7997MP	200MP	PET/Stainless Steel	24 (7)	94 (26)	232 (64)	
(2-5-0)		PET/Aluminum	32 (9)	75 (21)	262 (72)	
		PET/PET	39 (11)	66 (18)	257 (71)	
		PET/Polycarbonate	36 (10)	68 (19)	135 (27)	

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Double Linered Adhesive Transfer Tapes (for selective die cutting)

		Cohesion Static Shear ASTM D3654, 0.5 in ²			
3M™ Membrane Switch Product	Adhesive Family		72°F (22°C)/1000g	158°F (70°C)/500g	
Number	-	Film / Substrate	Typical Value Minutes	Typical Value Minutes	
7952MP 7962MP (2-0-0)	200MP	PET/Stainless Steel	10,000+	10,000+	
7953MP (1.5-0.5-1.5)	200MP	PET/Stainless Steel	10,000+	10,000+	
7955MP 7965MP (5-0-0)	200MP	PET/Stainless Steel	10,000+	10,000+	

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Double Coated Membrane Switch Spacers (for circuit separation)

3M™ Membrane		Cohesion Static Shear ASTM D3654, 0.5 in ²					
Switch Product Number	Adhesive Family		72°F (22°C)/1000g	158°F (70°C) / 500g			
Number		Film / Substrate	Typical Value Minutes	Typical Value Minutes			
7945MP 9045MP (2-1-2)	200MP	PET/Stainless Steel	10,000+	10,000+			
7956MP 9056MP (2-2-2)	200MP	PET/Stainless Steel	10,000+	10,000+			
7957MP 9057MP (2-3-2)	200MP	PET/Stainless Steel	10,000+	10,000+			
7959MP 9059MP (2-5-2)	200MP	PET/Stainless Steel	10,000+	10,000+			
7961MP 9061MP (2-7-2)	200MP	PET/Stainless Steel	10,000+	10,000+			

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Single Coated Membrane Switch Spacers (for circuit separation)

3M™ Membrane		Cohesion Static Shear ASTM D3654, 0.5 in ²				
Switch Product	Adhesive Family		72°F (22°C)/1000g	158°F (70°C) / 500g		
Number		Film / Substrate	Typical Value Minutes	Typical Value Minutes		
7993MP (2-1-0)	200MP	PET/Stainless Steel	10,000+	10,000+		
7995MP (2-3-0)	200MP	PET/Stainless Steel	10,000+	10,000+		
7997MP (2-5-0)	200MP	PET/Stainless Steel	10,000+	10,000+		

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Double Linered Adhesive Transfer Tapes (for selective die cutting)

3M™ Membrane		Cohesion Dynamic Shear ASTM D1001, 1 in ²		Tensile Strength (Yield) ASTM D2370		
Switch	Adhesive Family	158°F (70°	C)/500G	72°F (22°C)	
Product Number	-	Film / Substrate	Typical Value	Sample Thickness Mils (Microns)	Typical Value PSI	
7952MP	200MP	PET/Stainless Steel	103 (0.72)	2 (50)	51	
7962MP		PET/Polycarbonate	80 (0.55)			
(2-0-0)						
7953MP	200MP	PET/Stainless Steel	105 (0.72)	3.5 (88)	1593	
(1.5-0.5-1.5)		PET/Polycarbonate	88 (0.61)			
7955MP	200MP	PET/Stainless Steel	97 (0.67)	5 (125)	51	
7965MP		PET/Polycarbonate	80 (0.55)	·		
(5-0-0)						

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Double Coated Membrane Switch Spacers (for circuit separation)

3M™ Membrane		Cohesion Dyn ASTM D1001,	amic Shear I in ² (1 in. sq.)	Tensile Strength (Yield) ASTM D2370 72°F (22°C)		
Switch	Adhesive Family	158°F (70)°C)/500G			
Product Number	_	Film / Substrate	Typical Value	Typical Value Mils (Microns)	Typical Value	
7945MP	200MP	PET/Stainless Steel	68 (0.47)	5 (125)	2556	
9045MP		PET/Polycarbonate	70 (0.48)			
(2-1-2)						
7956MP	200MP	PET/Stainless Steel	103 (0.72)	6 (150)	3971	
9056MP		PET/Polycarbonate	78 (0.54)			
(2-2-2)						
7957MP	200MP	PET/Stainless Steel	79 (0.55)	7 (175)	5062	
9057MP		PET/Polycarbonate	66 (0.46)			
(2-3-2)						
7959MP	200MP	PET/Stainless Steel	78 (0.54)	9 (225)	6462	
9059MP		PET/Polycarbonate	69 (0.48)			
(2-5-2)						
7961MP	200MP	PET/Stainless Steel	76 (0.52)	11 (275)	7945	
9061MP		PET/Polycarbonate	66 (0.46)			
(2-7-2)						

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Single Coated Membrane Switch Spacers (for circuit separation)

3M™ Membrane	Adhesive Family	Cohesion Dynamic Shear ASTM D1001, 1 in ² (1 in. sq.) 158°F (70°C)/500G		Tensile Strength (Yield) ASTM D2370	
Switch Product				72°F (22°C)	
Number		Film / Substrate	Typical Value	Typical Value Mils (Microns)	Typical Value
7993MP	200MP	PET/Stainless Steel	N/A	3 (75)	3609
(2-1-0)		PET/Polycarbonate	N/A		
7995MP	200MP	PET/Stainless Steel	N/A	5 (125)	6749
(2-3-0)		PET/Polycarbonate	N/A		
7997MP	200MP	PET/Stainless Steel	N/A	7 (175)	6273
(2-5-0)		PET/Polycarbonate	N/A		

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Double Linered Adhesive Transfer Tapes (for selective die cutting)

3М™	Adhesive Family	Dielectic Strength ASTM D149,	Dielectic Constant/ Dissipation Factor	Volume/Surface Resistivity	
Membrane Switch Product		Short time method (air)	ASTM D150 72°F (22°C)	ASTM D257 72°F (22°C)	
Number		Typical Value Volts/Mil	Typical Value D.C. / D.F.	Typical Value V.R. Ohm - cm	Typical Value S.R. Ohms
7952MP 7962MP (2-0-0)	200MP	880	3.40 / 0.021	1.0 x 10 ¹⁵	> 5.6 x 10 ¹⁶
7953MP (1.5-0.5-1.5)	200MP	1400	3.29/0.017	5.8 x 10 ¹⁴	> 5.6 x 10 ¹⁶
7955MP 7965MP (5-0-0)	200MP	600	4.06 / 0.022	1.1 x 10 ¹⁵	> 5.6 x 10 ¹⁶

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Double Coated Membrane Switch Spacers (for circuit separation)

3M™ Membrane	Adhesive Family	Dielectic Strength ASTM D149, Short time method (air)	Dielectic Constant/ Dissipation Factor	Volume/Surface Resistivity	
Switch Product			ASTM D150 72°F (22°C)	ASTM D257 72°F (22°C)	
Number		Typical Value Volts/Mil	Typical Value D.C. / D.F.	Typical Value V.R. Ohm - cm	Typical Value S.R. Ohms
7945MP 9045MP (2-1-2)	200MP	1500	3.48 / 0.016	5.7 x 10 ¹⁴	> 5.6 x 10 ¹⁶
7956MP 9056MP (2-2-2)	200MP	1700 P	3.40 / 0.015	8.9 x 10 ¹⁴	> 5.6 x 10 ¹⁶
7957MP 9057MP (2-3-2)	200MP	1700 P	3.33 / 0.013	1.3 x 10 ¹⁵	> 5.6 x 10 ¹⁶
7959MP 9059MP (2-5-2)	200MP	1600 P	3.32 / 0.011	1.5 x 10 ¹⁵	> 5.6 x 10 ¹⁶
7961MP 9061MP (2-7-2)	200MP	1500	3.42 / 0.010	2.2 x 10 ¹⁵	> 5.6 x 10 ¹⁶

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Single Coated Membrane Switch Spacers (for circuit separation)

3М™	Adhesive Family	Dielectic Strength ASTM D149,	Dielectic Constant/ Dissipation Factor	Volume/Surface Resistivity		
Membrane Switch Product		Short time method (air)	ASTM D150 72°F (22°C)	ASTM D257 72°F (22°C)		
Number		Typical Value Volts/Mil	Typical Value D.C. / D.F.	Typical Value V.R. Ohm - cm	Typical Value S.R. Ohms	
7993MP (2-1-0)	200MP	1700	2.77/0.012	2.7 x 10 ¹⁵	> 5.6 x 10 ¹⁶	
7995MP (2-3-0)	200MP	1700	3.03/0.009	3.3 x 10 ¹⁵	> 5.6 x 10 ¹⁶	
7997MP (2-5-0)	200MP	1700	3.05 / 0.008	4.8 x 10 ¹⁵	> 5.6 x 10 ¹⁶	

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Double Linered Adhesive Transfer Tapes (for selective die cutting)

3M™ Membrane		Insulation & Moisture Resistance	Coefficient of Thermal Expansion	
Switch Product Number	Adhesive Family	Mil-I-46058C (100VDC, 60 sec.)	ASTM D696 25-175°C	
Number		Typical Value Ohms	Typical Value M/M/°C	
7952MP 7962MP (2-0-0)	200MP	1.3 x 10 ¹³	7.2 x 10 ⁻⁴	
7953MP 1.5-0.5-1.5)	200MP	1.7 x 10 ¹³	6.7 x 10 ⁻⁴	
7955MP 7965MP (5-0-0)	200MP	8.8 x 10 ¹²	9.2 x 10 ⁻⁴	

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Double Coated Membrane Switch Spacers (for circuit separation)

3M™ Membrane Switch Product Number	Adhesive Family	Insulation & Moisture Resistance	Coefficient of Thermal Expansion
		Mil-I-46058C (100VDC, 60 sec.)	ASTM D696 25-175°C
		Typical Value Ohms	Typical Value M/M/°C
7945MP 9045MP (2-1-2)	200MP	1.0 x 10 ¹³	6.1 x 10 ⁻⁴
7956MP 9056MP 2-2-2)	200MP	1.1 x 10 ¹³	5.1 x 10 ⁻⁴
7957MP 9057MP (2-3-2)	200MP	1.1 x 10 ¹³	5.4 x 10 ⁻⁴
7959MP 9059MP (2-5-2)	200MP	1.9 x 10 ¹³	4.7 x 10 ⁻⁴ 9059MP (2-5-2)
7961MP 9061MP (2-7-2)	200MP	1.6 x 10 ¹³	4.1 x 10 ⁻⁴ 9061MP (2-7-2)

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Typical Physical, Mechanical, and Electrical Properties and Performance Characteristics (continued)

3M™ Single Coated Membrane Switch Spacers (for circuit separation)

3M™ Membrane		Insulation & Moisture Resistance	Coefficient of Thermal Expansion	
Switch Product Number	Adhesive Family	Mil-I-46058C (100VDC, 60 sec.)	ASTM D696 25-175°C	
Number		Typical Value Ohms	Typical Value M/M/°C	
7993MP (2-1-0)	200MP	6.5 x 10 ¹²	4.5 x 10 ⁻⁴	
7995MP (2-3-0)	200MP	9.4 x 10 ¹²	3.9 x 10 ⁻⁴	
7997MP (2-5-0)	200MP	6.5 x 10 ¹²	2.8 x 10 ⁻⁴	

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Environmental Performance

Humidity Resistance – High humidity has a minimal effect on adhesive performance. Bond strength shows no significant reduction after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

UV Resistance – When properly applied, nameplates and decorative trim parts are not adversely affected by outdoor exposure.

Water Resistance – Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.

Temperature Cycling Resistance – High bond strength is maintained after cycling four times through:

- 4 hours at 158°F (70°C)
- 4 hours at -20°F (-29°C)
- 4 hours at 73°F (22°C)

Chemical Resistance – When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids and alkalis.

Bond Build-up: The bond strength of 3MTM High Performance Acrylic Adhesive increases as a function of time and temperature as the adhesive further wets the surface and reaches maximum bond strength after 72 hours at room temperature.

Temperature/Heat Resistance: 3MTM High Performance Acrylic Adhesive on polyester carriers is usable for short periods (minutes, hours) at temperatures up to 300 °F (149°C) and for intermittent longer periods (days, weeks) up to 250°F (121°C).

Lower Temperature Service Limit: -40°F (-40°C).

Application Ideas

• 3MTM Single Coated Membrane Switch Spacers are ideal for circuit layers, metal dome placement and lead protection

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Storage

It is suggested that products are stored at room temperature conditions of 70°F (21°C) and 50% relative humidity.

Shelf Life

If stored properly, product retains its performance and properties for 18 months from date of shipment.

Recognition/Certification

TSCA: This product is defined as an article under the Toxic Substances Control Act and therefore, it is exempt from inventory listing requirements

MSDS: 3M has not prepared a MSDS for this product which is not subjected to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R.1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, this product should not present a health and safety hazard. However, use or processing of the product in a manner not in accordance with the directions for use may affect its performance and present potential health and safety hazards.

UL: These products have been recognized by Underwriters Laboratories, Inc. under UI 746C and UL 969. For more information on the UL Certification, please visit the website at http://www.3M.com/converter, select UL Recognized Materials, then select the specific product area.

Note: One of 3M's core values is to respect our social and physical environment. 3M is committed to comply with ever-changing, global, regulatory and consumer environmental, health, and safety (EHS) requirements. As a service to our customers, 3M is providing information on the regulatory status of many 3M products. Further regulation information including that for OSHA, USCPSI, FDA, California Proposition 65, READY and RoHS, can be found at 3M.com/regs.

Technical Information

The technical information and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. It has been prepared from testing that was performed using standard test methods, and tested equipment that is calibrated in compliance to ISO9001 and operated by trained professionals in controlled environments. The data should be considered representative or typical only and should not be used for specification purposes. 3M reserves the right to make changes to the design, construction and technical data of products without prior warning.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluation the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

7945MP, 7952MP, 7953MP, 7955MP, 7956MP, 7957MP, 7959MP, 7961MP, 7962MP, 7965MP, 7993MP, 7995MP, 7997MP, 9045MP, 9056MP, 9057MP, 9059MP, 9061MP

Warranty, Limited Remedy and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence, or strict liability.



This Industrial Adhesives & Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



For more information contact your local 3M representative or call 800-223-7427



Industrial Adhesives & Tapes Division Converter Markets 3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-223-7427 651-778-4244 (fax) www.3M.com/converter

3M is a trademark of 3M Company © 3M 2013 (10/13)